



**GEOTEX<sup>®</sup> 1701** is a polypropylene, staple fiber, needlepunched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needled to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 1701** conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

MARV <sup>2</sup>			
PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>ORIGIN OF MATERIALS</b>			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
<b>PHYSICAL</b>			
Mass/ Unit Area	ASTM D-5261	16.0 oz/yd <sup>2</sup>	542 g/m <sup>2</sup>
Thickness	ASTM D-5199	165 mils	4.2 mm
<b>MECHANICAL</b>			
Tensile Strength (Grab)	ASTM D-4632	390 lbs	1735 N
Elongation	ASTM D-4632	50%	50%
Puncture	ASTM D-4833	250 lbs	1112 N
CBR Puncture	ASTM D-6241	1125 lbs	5006 N
Mullen Burst	ASTM D-3786	800 psi	5515 kPa
Trapezoidal Tear	ASTM D-4533	155 lbs	690 N
<b>ENDURANCE</b>			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
<b>HYDRAULIC</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	100 US Std. Sieve	0.150 mm
Permittivity	ASTM D-4491	0.7 sec <sup>-1</sup>	0.7 sec <sup>-1</sup>
Permeability	ASTM D-4491	0.27 cm/sec	0.27 cm/sec
Water Flow Rate	ASTM D-4491	50 gpm/ft <sup>2</sup>	2037 l/min/m <sup>2</sup>
<b>ROLL SIZES</b>		15 ft x 300 ft	4.57 m x 91.5 m

**NOTES:**

- The property values listed above are effective 04/2011 and are subject to change without notice.
- Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
- Maximum average roll value.

