

VOLCLAY® SOIL SEALANT TG-50

TECHNICAL DATA SHEET

DESCRIPTION	Volclay TG-50 is a treated, granular, high swelling Wyoming sodium bentonite for use in contaminated environments.	
APPLICATIONS	Soil/bentonite liners; general sealing applications	
COMPOSITION	Sodium bentonite is a hydrous silicate of alumina primarily consisting of the clay mineral montmorillonite, which swells several times its own volume when wetted.	
FREE SWELL	24 ml/2g minimum (ACC 1010)	
FILTRATE LOSS	18 ml maximum (API 13A)	
MOISTURE CONTENT	12 percent maximum as shipped	
PARTICLE SIZING	5 percent max. retained on a #10 mesh (2.00 mm) sieve 15 percent max. passing a #200 mesh (75 µm) sieve (ASTM D422)	
DRY BULK DENSITY	65 lbs/ft ³ (1,040 kg/m ³) typical	
PACKAGING	50-lb (22.5-kg) multi-wall paper bags; 2000lb (900kg) or 4,000 lb (1,800-kg) super sacks; or bulk.	
AVAILABILITY	F.O.B. Lovell, WY. Quantities less than 1 ton may be available locally.	
APPLICATION INFORMATION:	Primary Soil Type	Typical Application Rate*
	Sand	8-10 lbs/ft ² (40-50 kg/m ²)
	Silt	4-8 lbs/ft ² (20-50 kg/m ²)
	Clay	2-4 lbs/ft ² (10-20 kg/m ²)
	*Application rates are for a soil/bentonite liner mixed in a layer 6 inches (150mm) in thickness with a permeability of 1×10^{-7} cm/sec. Application rates above are shown for informational purposes only. All soils should be tested to determine specific application rates and compatibility requirements.	

LAST UPDATED AUGUST 2009

IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.



www.CETCO.com

2870 Forbs Avenue Hoffman Estates, IL 60192
847.851.1800 | 800.527.9948